



GREASES AND COMPOUND PRODUCT INFORMATION CHART

Product	Appearance	Specific Gravity	Penetration	Bleed	Evaporation	Thermal Conductivity Btu/ft ² h ⁰ F/in.	Temperature Range °C
V-711 ⁽¹⁾	Translucent White	1.03	250	0.25%	1.3%	1.2	-40 to 204
V-724 ⁽²⁾	Translucent White	1.03	260	5%	1.4%	1.08	-58 to 204
V-726 ⁽²⁾	Translucent, Homogeneous	1.03	330	1.0%	0.7%	0.96	-40 to 204
V-735 ⁽²⁾	White-translucent, Homogeneous	1.04	230	2.1%	1.1%	N/A	-65 to 204
V-740 ⁽⁴⁾	White, Opaque, Homogeneous	2.45	257	0.5%	0.5%	4.8	-40 to 204
V-742 ⁽⁴⁾	White, Opaque, Homogeneous	2.9	230	0%	0.7%	8.4	-55 to 175
V-755 ⁽⁵⁾	Light pink, Homogeneous	1.00	280	2.0%	0.5%	N/A	-65 to 177
V-761F ⁽³⁾	Light tan, Homogeneous	0.99	86,000 (Viscosity)	10%	0.2%	N/A	-73 to 204
V-769 ⁽⁵⁾	Green, Homogeneous	1.0	320	2.7%	0.2%	N/A	-68 to 204
GREASE 33 ⁽⁵⁾	Brown, Homogenous	1.03	280	2.5%	2.5%	2.8 10 ⁻⁴	-71 to 175

1. GENERAL PURPOSE COMPOUND
2. DIELECTRIC COMPOUND
3. FLUID LUBRICATING GREASE
4. THERMALLY CONDUCTIVE COMPOUND
5. LUBRICATING GREASE