

# VI-SIL™ V-1056

April 1998

TECHNICAL DATA SHEET

## PRODUCT DESCRIPTION

VI-SIL V-1056 is a high strength, two component, tin catalyzed, room temperature cured silicone rubber. It is designed as a 25 Shore A, low viscosity, very pourable compound providing excellent cured rubber properties. V-1056 has proven to be an excellent product for use in making rigid polyurethane foam picture frames and mirrors.

## PRODUCT FEATURES AND BENEFITS

- High strength properties
- 25 Shore A - Flexible
- Low viscosity for easy pour
- Excellent detail reproduction
- Color contrast to ensure thorough mixing

## TYPICAL APPLICATIONS

- Mirror and picture frame casting with rigid polyurethane foam
- General purpose moldmaking

## TYPICAL PROPERTIES - AS SUPPLIED

### Part A - Base Component

- |                         |        |
|-------------------------|--------|
| • Color                 | White  |
| • Viscosity, cP.(mPa.s) | 34,000 |

### Part B - Catalyst Component (Std Catalyst)

- |         |      |
|---------|------|
| • Color | Blue |
|---------|------|

## TYPICAL CATALYZED PROPERTIES

Mixed at 24°C (75°F) and 50% R.H.

- |  |        |
|--|--------|
| • Mix Ratio, A:B (By Weight)                     | 10:1   |
| • Viscosity, cP.(mPa.s)                          | 16,000 |
| • Pot Life, Hrs. (1)                             | 4      |
| • Demold Time, Hrs. (24°C)                       | 24     |
| • 72 Hour Thick Section<br>Hardness, Shore A (2) | 24     |

## TYPICAL PROPERTIES OF CURED RUBBER

Cured 7 days at 24°C and 50% R.H.

- |   |                               |
|---|-------------------------------|
| • Color   | Blue                          |
| • Specific Gravity  | 1.09                          |
| • Hardness (Shore A)<br>ASTM D2240                        | 23                            |
| • Tensile Strength, psi (N/mm <sup>2</sup> )<br>ASTM D412 | 490 (3.4)                     |
| • Elongation, %<br>ASTM D412                              | 325                           |
| • Tear Resistance, ppi (N/mm)<br>ASTM D624, Die B         | 100 (17.5)                    |
| • Coverage, cu. in./lb (cc/kg)                            | 25.4 (909)                    |
| • Temperature Range                                       | -50 to 150°C<br>(-8 to 302°F) |

## SHELF LIFE

Six (6) months from date of shipment when stored at 24°C (75°F) in original unopened containers.

- (1) Time at which material gels.  
(2) 0.5 in (1.27 cm) thick cup specimen.

**NOT FOR PRODUCT SPECIFICATION:** The technical data contained herein are intended for reference only and **are not** intended for use in preparing sales specifications. For assistance and recommendations on sales specifications for this product, contact RHODIA VSI at (800) 356-7560 or (518) 285-6300.



## MIXING GUIDELINES FOR VI-SIL™ TWO-COMPONENT TIN CURE MOLDMAKING SYSTEMS

1. Stir the base (Part A) well before use (except when machine dispensing).
2. Shake the catalyst container (Part B) well before use.
3. Weigh the desired amount of base into a clean mixing container. Tip the container and roll the base all the way around the side wall up to two inches from the top. This will prevent the catalyst from becoming absorbed into the container. It is recommended that the container be filled to not more than 1/3 the container depth to allow sufficient room for expansion during the deaeration procedure.
4. Weigh the proper amount of catalyst into the container. Mix the base and catalyst together by stirring with a stiff, flat ended metal spatula until a uniform color is obtained. Scrape the container walls and bottom well to insure a thorough mix.
5. Place the container into a vacuum chamber and evacuate the entrapped air from the mixture using a vacuum pump capable of achieving 29 inches of mercury vacuum. The mixture will rise, crest and then collapse in the container. Interruption (bumping) of the vacuum may be necessary to prevent overflowing the container. Keep the mixture under full vacuum for 2-3 minutes after the material has receded in the container.
6. Bleed air slowly into the vacuum chamber. When the chamber is at atmospheric equilibrium, remove the cover plate and take out the container.
7. Pour the deaired material slowly in a steady stream from one end of the mold box so that the material flows evenly over the pattern. This should minimize entrapment of air bubbles under the flowing material. A "print" coat may be poured first over the pattern which will also help reduce the possibility of entrapping air on the pattern and in the cured rubber. A mold release (petroleum jelly) may be applied on the pattern first to improve release.
8. Allow the rubber to cure for 16-24 hours at 75±5°F (24°C) before removing the cured rubber mold from the pattern. Heat acceleration is not recommended with this product.
9. For best results, allow the mold to air cure an additional 24 hours before using it in production. Full cure is achieved in 3-7 days.
10. For bonding to wood or metals, use VI-SIL™ V-04 primer. Follow recommendations on V-04 technical data sheet for best results.

### PROCESSING INFORMATION

#### CATALYZED PROCESSING PROPERTIES ARE AFFECTED BY TEMPERATURE AND HUMIDITY VARIATION

1. For best results, mix and cure the material at 75°F (24°C) and 50% relative humidity.
2. Higher temperature and humidity will decrease the work life and pot life of the material. The faster cure will also affect the flow properties. Refrigeration of the base prior to use in hot environments has shown to improve the handling properties of this material.
3. Lower temperatures and humidity will increase the work life and pot life of the material. The slower cure will increase the flow time. Cure temperatures below 68°F (20°C) are not recommended and have been found to cause a reduction in final cure hardness and properties.
4. It is important that the catalyst containers are tightly closed after use. Catalyst exposed to air for extended periods of time will hydrolyze (cure). An indication of hydrolysis is a film or crust formation on the surface of the catalyst. The use of hydrolyzed catalyst is not recommended and may cause incomplete cure.

### SAFETY PRECAUTIONS

#### USE MATERIAL IN ACCORDANCE WITH MATERIAL SAFETY DATA SHEET

This rubber system uses an organometallic tin catalyst which may irritate or burn skin and eyes upon contact. If eye contact occurs, flushing with water for at least 15 minutes should relieve discomfort. If irritation or discomfort persists, obtain medical attention. KEEP PRODUCT AWAY FROM CHILDREN. Contact RHODIA VSI Customer Service (800) 356-7560 to obtain an MSDS for this product.

**FOR THE NAME OF YOUR NEAREST RHODIA VSI SALES REPRESENTATIVE OR DISTRIBUTOR, AND FOR TECHNICAL ASSISTANCE ON THIS PRODUCT AND OTHER RHODIA VSI PRODUCTS, CONTACT CUSTOMER SERVICE AT (800) 356-7560**

**NOTE:** The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. RHODIA VSI GUARANTEES THAT ITS PRODUCTS COMPLY WITH ITS SALES SPECIFICATIONS. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document and RHODIA VSI is at their disposal to supply any additional information.

VI-SIL™ is a Trademark of Rhodia Inc.

Rhodia VSI is Registered to ISO 9001



405 JORDAN ROAD  
TROY, NY 12180  
TEL: 800-356-7560 -- 518-285-6300 -- FAX: 518-285-6346

---