

# PRETHANE

## URETHANE SYSTEMS

### PHYSICAL PROPERTIES COMPARISON CHART

	PC-00	PC-10	PC-20	PC-30	PC-40	PC-50	PC-55	PC-65	PC-70
<b>MIX RATIO BY WEIGHT</b>	100A/97B (1:1 by vol)	100A/100B	100A/100B	100A/100B	100A/100B	100A/100B (1:1 by vol)	100A/98B (1:1 by vol)	100A/97B (1:1 by vol)	100A/50B
<b>SHORE HARDNESS</b>	0 A	10 A	20 A	30 A	40 A	50 A	55 A	65 A	70 A
<b>POUR TIME, MINIMUM</b>	30 min	30 min	20 min	20 min	20 min	8-10 min	5-7 min	5-7 min	5-7 min
<b>DEMOLD TIME @ 72 F</b>	8 hours	8 hours	4-6 hours	3-5 hours	2-4 hours	2-4 hours	1-2 hours	1-2 hours	1-2 hours
<b>COLOR</b>	Off White	Off White	Pink	Green	Blue	Trans-lucent	Gray	Tan	Blue
<b>VISCOSITY, MIXED</b>	1,100	2,200	1,100	1,100	1,100	1,100	1,400	1,400	2,200
<b>CUBIC INCHES PER POUND</b>	25.61	25.61	25.78	25.81	26	26.16	26.13	26.19	26.67
<b>SPECIFIC GRAVITY, CURED</b>	1.068	1.068	1.068	1.068	1.068	1.068	1.068	1.068	1.07
<b>SHRINKAGE DURING CURE</b>	0.0015 in	0.0015 in	0.0015 in	0.0015 in	0.0015 in	0.0015 in	0.0015 in	0.0015 in	0.0015 in